

Fig. 1 Results of freeze casting simulation in 20%, 30% and 40% concentrations.

To further study the dendritic patterns on toughness, we choose three cases(case 1 to 3) to compare different shapes of dendrites (Fig. 3).Microstructures in these cases are taken directly from features in freeze casting microstructure to produce the RVE. Notice that, in order to maintain the criterion of these microstructures, the spatial density is kept in the same value.




Fig. 2 Stress strain curve for different microstructures




Fig. 3 Damage of the microstructure and the selected cases for further analysis

Left of Fig. 4 compares case 1 to 3 with the original freeze casting microstructure. It shows that dendrites do influence the property, but not all dendrite is beneficial for toughness, like case1. Case 3, which seems to process less dendrite, is actually tougher than the other cases. We notice that the case 2 does not fail at a sudden. It is implied that the shape of dendrites seems to be an important parameter. We thus further extract a single dendrite to explore the impact of shape.

By observing the crack development, we choose three cases (Fig. 3). The analysis results show that the shape of dendrites play an important role of toughness. Case 5 and case 6 process a better toughness comparing to case 3. (Fig. 4). All failure patterns are shown in Fig. 5.

Case 3 to 6




Fig. 4 Stress strain curve for six cases, including comparing first three cases with original freeze casting microstructure (left) and comparing last three cases with case 3.




Fig. 5 Failure patterns of all the six cases studied herein.

4. CONCLUSION

In this study, a virtual processing for freeze casting based on a phase-field model is developed. A virtual testing adapting the concept of RVE is developed to investigate the stress distribution, load transmission as well as crack propagation due to different microstructures from freeze casting. We show that the level of dendrites is an important controlled parameter of the toughness. Furthermore, the dendritic patterns play an important role for toughness.

REFERENCES

- [1] Etienne Munch, Maximilian E Launey, Daan H Alsem, Eduardo Saiz, Antoni P Tomsia, and Robert O Ritchie. Tough, bio-inspired hybrid materials. *Science*, 322(5907):1516–1520, 2008.

- [2] Marc André Meyers, Po-Yu Chen, Albert Yu-Min Lin, and Yasuaki Seki. Biological materials: structure and mechanical properties. *Progress in Materials Science*, 53(1):1–206, 2008.
- [3] Ulrike GK Wegst, Matthew Schecter, Amalie E Donius, and Philipp M Hunger. Biomaterials by freeze casting. *Philosophical Transactions of the Royal Society of London A: Mathematical, Physical and Engineering Sciences*, 368(1917):2099–2121, 2010.
- [4] Sylvain Deville, Eduardo Saiz, Ravi K Nalla, and Antoni P Tomsia. Freezing as a path to build complex composites. *Science*, 311(5760):515– 518, 2006.
- [5] Sylvain Deville, Eric Maire, Audrey Lasalle, Agnès Bogner, Catherine Gauthier, Jérôme Leloup, and Christian Guizard. In situ x-ray radiography and tomography observations of the solidification of aqueous alumina particle suspensions—part i: Initial instants. *Journal of the American Ceramic Society*, 92(11):2489–2496, 2009.
- [6] Ulrike GK Wegst, Hao Bai, Eduardo Saiz, Antoni P Tomsia, and Robert O Ritchie. Bioinspired structural materials. *Nature materials*, 14(1):23–36, 2015.
- [7] T-H Huang, T-H Huang, Y-S Lin, C-H Chang, P-Y Chen, S-W Chang, C-S Chen (2017) “Phase-Field Modeling of Microstructural Evolution by Freeze-Casting,” *Advanced Engineering Materials*, accepted.
- [8] Nikolas Provatas, Nigel Goldenfeld, and Jonathan Dantzig. Efficient computation of dendritic microstructures using adaptive mesh refinement. *Physical Review Letters*, 80(15):3308, 1998.
- [9] Kumar K Tamma, Masao Shimada, Siti Ujila Binti Masuri, and Xiangmin Zhou. Computer-implemented method for performing simulation, June 25 2014. US Patent App. 14/314,925.
- [10] M Shimada, A Hoitink, and KK Tamma. The fundamentals underlying the computations of acceleration for general dynamic applications: Issues and noteworthy perspectives. *CMES: Computer Modeling in Engineering & Sciences*, 104(2):133–158, 2015.
- [11] William J Boettinger, James A Warren, Christoph Beckermann, and Alain Karma. Phase-field simulation of solidification. *Materials Research*, 32(1):163, 2002.
- [12] Alain Karma. Phase-field formulation for quantitative modeling of alloy solidification. *Physical Review Letters*, 87(11):115701, 2001.
- [13] Blas Echebarria, Roger Folch, Alain Karma, and Mathis Plapp. Quantitative phase-field model of alloy solidification. *Physical Review E*, 70(6):061604, 2004.
- [14] H. Moulinec and P. Suquet, *Computer methods in applied mechanics and engineering*, 1998, 157, 69–94
- [15] M. Li, W. Shen and J. Shao, *Mechanics of Materials*, 2016, 92, 275–288.